


STAIRCARE SC-R UV PROTECTION



TAILOR MADE FRP SOLUTIONS FOR
A LARGE RANGE OF INDUSTRIES SINCE 2004




STAIRCAREFRP
COMPOSITE DESIGN & FABRICATION

Staircare SC-R UV Protection

■ UV Protection

UV inhibitors are mixed into the resin and also into a synthetic surfacing veil that is incorporated ensuring optimum protection from UV radiation and the harsh outdoors.

As an option Staircare offers an additional UV coating that can be applied to products with extreme UV exposure, such as off-shore platforms etc.




■ UV Test Reports

Accelerated weathering testing in accordance with ASTM G 154 and test for colour fastness ISO 105 – A02 1993/COR 2:2005 have been conducted on Staircare SC-R 50 x 50 x 5mm FRP square hollow section and SC-R 38 x 38 x 38mm thick square mesh with girt.

According to ISO 105 – A02: 1993/ COR 2: 2005 the grey scale was determined under standard light with scale 5 as the best and scale 1 as the worst.

SC-R 50 X 50 X 5mm FRP Square Hollow Section Light Aging Test – UV Exposure: Grey Scale Score 4



TEST REPORT

No. : SUIN1906004271MR
 Date : Jul 05, 2019
 Page: 3 of 5

Test Item: Light Ageing Test-UV Exposure
 Sample Description: Yellow plastic parts
 Test Method: ASTM G154-16 Cycle 1
 Test Condition:

Exposure cycle:
 ASTM G154-16 Cycle 1
 Lamp type: UVA-340
 8h UV at (60±3)°C BPT, (0.89±0.02)W/(m²·nm)@340nm
 4h condensation at (50±3)°C BPT


Exposure duration: 400h

Test Result:

Test Item	Grey scale
Light Ageing Test-UV Exposure	4

Note:

- According to ISO 105-A02:1993/Cor.2:2005, the grey scale was determined under the D65 standard light, with scale 5 as the best and scale 1 as the worst.
- The results were carried out within 1 hour after above specified durations for the intermediate inspection as well as at the end of the exposure.




Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com>. Terms and Conditions apply and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/sgs-services/sgs-computerized-testing-document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained herein reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not constitute parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

SGS S.p.A. Via Salaria 439, 00198 Roma, Italy
 中国 苏州 工业园区金鸡湖东大街121号 邮编: 215021 中国 北京 朝阳区望京东二街10号 邮编: 215021 中国 香港 干诺道中189号11楼 邮编: 215021

Member of the SGS Group (SGS SA)





SC-R 50 X 50 X 5mm FRP Square Hollow Section Light Aging Test – UV Exposure: Grey Scale Score 4




TEST REPORT

No. : SUIN1906004271MR
Date : Jul 05, 2019
Page: 4 of 5

Test Photo:

	
Original sample	Reference sample Test sample Before test
	
Reference sample Test sample After test	Reference sample Test sample The close-up after test




Unless otherwise agreed to writing, this document is issued by the Company subject to its General Conditions of Service printed hereon, available on request on electronic or paper form. Unless specified by Terms and Conditions apply and, for all other formal documents, subject to Terms and Conditions for Electronic Documents of <http://www.sgs.com/zh-tw/sgs-conditions-service>. All rights reserved. All information contained herein reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not constitute parties to a transaction from assuming all their rights and obligations under the transaction documents. This document cannot be reproduced or used in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Address: 12, New Kowloon Road, No. 75, High Street, 19F, Suite, China 210201 T (86-512) 82988200 F (86-512) 82988212 www.sgs.com.cn
 中国苏州 工业路12号新科苑75号高街19楼1909室 邮编: 210201 T (86-512) 82988200 F (86-512) 82988212 e.sgs.china@sgs.com

Member of the SGS Group (SGS SA)

SC-R 38 x 38 x38mm thick FRP Sqaure Mesh Light Aging Test – UV exposure : Grey scale score 3 – 4



TEST REPORT

No. : SUIN1906004266MR
 Date : Jul 05, 2019
 Page: 3 of 5

Test Item: Light Ageing Test-UV Exposure
 Sample Description: Yellow plastic parts
 Test Method: ASTM G154-16 Cycle 1
 Test Condition:

Exposure cycle:
 ASTM G154-16 Cycle 1
 Lamp type: UVA-340
 8h UV at (60±3)°C BPT, (0.89±0.02)W/(m²·nm)@340nm
 4h condensation at (50±3)°C BPT


Exposure duration: 400h

Test Result:

Test Item	Sample size	Grey scale
Light Ageing Test-UV Exposure	38×38×38	3-4

Note:

- According to ISO 105-A02:1993/Cor.2:2005, the grey scale was determined under the D65 standard light, with scale 5 as the best and scale 1 as the worst.
- The results were carried out within 1 hour after above specified durations for the intermediate inspection as well as at the end of the exposure.



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed hereon, available on request or accessible at <http://www.sgs.com/portal/Forms-gsc-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/portal/Forms-gsc-Conditions/Terms-e-Document.aspx>. Attention is drawn to the limitation of liability, indemnification and arbitration clauses printed therein. Any holder of this document is advised that information contained herein reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not constitute parties to a transaction from assuming all their rights and obligations under the transaction document. This document cannot be reproduced, except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Building 12, New Industry Square, No.75 Jingde Street, SF, Suzhou, China, 215021 | (86-512) 62962010 | (86-512) 62962112 | www.sgs.com.cn
 中国苏州·工业园区中新苏台科技园75号厂房12楼 邮编: 215021 | (86-512) 62962010 | (86-512) 62962112 | sgs.china@sgs.com

Member of the SGS Group (SGS SA)





**SC-R 38 x 38 x38mm thick FRP Sqaure Mesh
Light Aging Test – UV exposure : Grey scale score 3 – 4**


SGS

TEST REPORT

No. : SUIN1906004266MR
Date : Jul 05, 2019
Page: 4 of 5

Test Photo:

	
Original sample	The close-up of sample size
	
Reference sample Test sample Before test	Reference sample Test sample After test



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed elsewhere available on request at <http://www.sgs.com/sgs> Terms and Conditions apply and, for Singapore based documents, subject to Terms and Conditions for Elements Documented at <http://www.sgs.com/sgs> Terms and Conditions (Terms and Conditions apply) wherever drawn to the attention of holders, sub-licensees and sub-contractors. Please refer to the back of the document for further information. The information contained herein reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions. It does not constitute a guarantee of accuracy. The Company's sole responsibility is to its Client and this document does not constitute part of a transaction from acquiring all their rights and obligations under the transaction documents. This document cannot be reproduced, stored or full, without prior written approval of the Company. Any unauthorized alteration, forgery or application of the printed or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

SGS (Singapore) Pte. Ltd. 11, Southview Road, Singapore 609568 www.sgs.com.sg 65-63566212



SGS (China) Pte. Ltd. No. 71, Jingde Street, SF, Suzhou, China 215021 1 (36-512) 6366200 1 (86-512) 6266212 www.sgs.com.cn 中国苏州 工业园区南园路71号 邮编: 215021 1 (36-512) 6366200 1 (86-512) 6266212 e.gpschina@sgs.com

Member of the SGS Group (SGS SA)

FRP COMPOSITES FABRICATION SERVICE, PROFILE AND GRATING SALES



STAIRCARE AUSTRALIA PTY LTD

 2/84 Old Pittwater Road, Brookvale NSW 2100, Australia
 +61 (2) 9939 3838

 www.staircare-frp.com.au
 info@staircare-frp.com.au